

IS : 4412 - 1981

(Reaffirmed 2021)

REAFFIRMED

Indian Standard
SPECIFICATION FOR COPPER WIRES FOR 2006
GENERAL ENGINEERING PURPOSES
(*First Revision*)

First Reprint OCTOBER 1991

UDC 669.3-426

© Copyright 1981

BUREAU OF INDIAN STANDARDS
MANAK BILAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

IS : 4412 - 1981

Indian Standard

SPECIFICATION FOR COPPER WIRES FOR GENERAL ENGINEERING PURPOSES

(First Revision)

Copper and Copper Alloys Sectional Committee, SMDC 11

Chairman

DR L. R. VAIDYANATH

Members

SHRI DEV KUMAR AGGARWAL

SHRI V. R. GADRE (Alternate)

SHRI S. N. BAFNA

SHRI N. M. BAFNA (Alternate)

SHRI J. NAGESH BHATT

SHRI A. DWARKANATH (Alternate)

SHRI V. N. BHIDE

SHRI S. K. MOHANTY (Alternate)

SHRI S. N. CHANDA

SHRI S. K. DAS

SHRI S. C. PAUL (Alternate)

SHRI P. GHOSH

SHRI TRILOK SINGH (Alternate)

SHRI A. K. GUHA

SHRI A. V. HARNE

SHRI T. MUKHERJEE (Alternate I)

SHRI K. N. WADHWA (Alternate II)

SHRI D. P. JAIN

SHRI D. N. CHAKRABORTY (Alternate)

SHRI S. L. JAIN

SHRI S. RAMAKRISHNAN (Alternate)

SHRI F. A. A. JARDANWALLA

SHRI C. CHATTERJEE (Alternate)

SHRI S. K. KHANDEKAR

SHRI A. S. SURYANARAIN (Alternate)

SHRI J. MARWAHA

DR S. K. BHOWAS (Alternate)

SHRI LAXAMAN MISRA

Representing

Indian Copper Information Centre, Calcutta

Bralco Metal Industries Pvt Ltd, Bombay

Coventary Metals Rajasthan Pvt Ltd, Jodhpur

Indian Telephone Industries Ltd, Bangalore

**Directorate General of Ordnance Factories,
Calcutta**

**Bengal Ingot Co Ltd, Calcutta
Ministry of Defence (DGI)/DPI (N)**

Indian Cable Co, Jamshedpur

**Directorate General of Supplies & Disposals,
New Delhi**

Bharat Heavy Electricals Ltd, Secunderabad

Saru Smelting Pvt Ltd, Meerut

Alcobex Metals (P) Ltd, Meerut

Indian Standard Metal Co Ltd, Bombay

Vanaz Engineers (P) Ltd, Pune

**Ministry of Steel & Mines, New Delhi; and
Hindustan Copper Ltd, Ghatila**

**Directorate General of Technical Develop-
ment, New Delhi**

(Continued on page 2)

© Copyright 1981

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act (XIV of 1957)* and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 4412 - 1981

(Continued from page 1)

<i>Members</i>	<i>Representing</i>
SHRI T. R. MOHAN RAO (<i>Alternate</i>)	
SHRI B. M. MISTRY	Ministry of Finance
SHRI A. K. MITRA	National Pipes & Tubes Co Ltd, Calcutta
SHRI S. V. NADKARNI	Advani Oerlikon Ltd, Bombay
SHRI S. K. SENGUPTA (<i>Alternate</i>)	
SHRI A. T. PAL	Ministry of Defence (R & D)
SHRI I. N. BHATIA (<i>Alternate</i>)	
SHRI H. S. PAROHI	Kamani Metals and Alloys Ltd, Bombay
SHRI A. H. SABHACHANDANI (<i>Alternate</i>)	
DR E. G. RAMACHANDRAN	Indian Institute of Technology, Madras
SHRI P. S. RAMASWAMY	Bhandary Metallurgical Corporation Pvt Ltd, Bombay
SHRI M. K. RAO	Indian Non-Ferrous Metals Manufacturers Association, Calcutta; and The Binani Metal Works Ltd, Calcutta
SHRI B. NAGCHAUDHURI (<i>Alternate</i>)	
REPRESENTATIVE	Institution of Engineers (India), Calcutta; and Khetri Copper Complex, Jodhpur
SHRI S. K. ROY	Ministry of Defence (DGI)
SHRI P. K. L. P. NIMANKAR (<i>Alternate</i>)	
SHRI D. K. SEHGAL	Leader Engineering Works, Jullundur
SHRI V. K. CHOUDHURY (<i>Alternate</i>)	
SENIOR CHEMIST & METALLURGIST, CENTRAL RAILWAY, BOMBAY	Ministry of Railways
DEPUTY DIRECTOR (MET) - II, RDSO, LUCKNOW (<i>Alternate</i>)	
SHRI S. C. SIVARAMAKRISHNAN	National Metallurgical Laboratory (CSIR), Jamshedpur
SHRI N. S. SURANA	Multimetals Ltd, Calcutta
SHRI S. S. VAIDYANATHAN	J. B. Metal Industries Pvt Ltd, Bombay
SHRI C. R. RAMA RAO, Director (Struc & Met)	Director General, ISI (<i>Ex-officio Member</i>)

Secretary
SHRI O. N. DASGUPTA
Deputy Director (Met), ISI

IS : 4412 - 1981

Indian Standard
SPECIFICATION FOR COPPER WIRES FOR
GENERAL ENGINEERING PURPOSES
(First Revision)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 29 May 1981, after the draft finalized by the Copper and Copper Alloys Sectional Committee had been approved by the Structural and Metals Division Council.

0.2 Copper wires are used in a number of engineering applications in the form of rivets, bolts and nuts, wire cloth and nails. This standard was earlier published in 1957. In this revision the following changes have been made:

- a) Scope of wire size has been extended;
- b) Only grade 1 with minimum changes in the chemical composition has been retained;
- c) For dimensions of wires, reference has been made to the relevant Indian standard; and
- d) Tensile properties have been specified.

0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard covers the requirements of copper wires for general engineering purposes.

2. TERMINOLOGY

2.0 For the purpose of this standard, the following definition of wire in addition to those given in IS : 3288 (Part I) - 1981† shall apply.

*Rules for rounding off numerical values (revised).

†Glossary of terms for copper and copper alloys: Part I Cast form and wrought form (main types) (second revision).

IS : 4412 - 1981

2.1 Wire — Rolled, extruded or drawn product of solid section of uniform cross section along its whole length and the distance between two parallel faces not exceeding 6 mm; may be supplied in straight length or in coils or on spools.

3. SUPPLY OF MATERIAL

3.1 General requirements relating to the supply of material shall conform to IS : 1387-1967*.

4. CHEMICAL COMPOSITION

4.1 Copper wires when analyzed in accordance with IS : 440-1964† shall conform to the requirements of IS : 191 (Part VIII) - 1980‡ as given in Table 1.

TABLE 1 CHEMICAL COMPOSITION

ELEMENT	PERCENT
Copper + Silver, <i>Min</i>	99.80
Phosphorus	0.015 - 0.10
Antimony, <i>Max</i>	0.005
Arsenic, <i>Max</i>	0.05
Bismuth, <i>Max</i>	0.003
Iron, <i>Max</i>	0.03
Lead, <i>Max</i>	0.01
Nickel, <i>Max</i>	0.10
Selenium + Tellurium, <i>Max</i>	0.02
Tellurium, <i>Max</i>	0.01
Tin, <i>Max</i>	0.01
Total of impurities excluding silver, nickel, arsenic and phosphorus, <i>Max</i>	0.06

5. PHYSICAL PROPERTIES

5.1 Tensile Test — The copper wires above 1 mm diameter when tested in accordance with IS : 2656-1964§ shall have the tensile properties as given in Table 2.

TABLE 2 TENSILE PROPERTIES

TEMPER	TENSILE STRENGTH MPa, <i>Min</i>	ELONGATION PERCENT ON 100 mm GAUGE LENGTH, <i>Min</i>
O (Annealed)	225	35
HB (Half hard)	280	—
HD (Hard)	340	—

NOTE — 1 MPa = 0.102 kgf/mm².

*General requirements for the supply of metallurgical materials (*first revision*).

†Methods of chemical analysis of copper (*revised*).

‡Specification for copper: Part VIII Phosphorized copper (DHP) (*third revision*).

§Method for tensile testing of copper and copper alloy wire.

IS : 4412 - 1981

5.2 Embrittlement Test – When required by the purchaser, the test pieces may be tested in accordance with the method given in 5.2.1.

5.2.1 Test pieces of suitable length shall be made from wires selected as per 8.3 and exposed to an atmosphere of hydrogen for a period of 30 minutes at a temperature of 825 to 875°C after which they shall be cooled in the container itself (out of contact with air). Each test piece is to be bent steadily at right angle and flattened close. There shall be no sign of cracks or flaws on the pieces so tested.

6. FREEDOM FROM DEFECTS

6.1 The wires shall be clean, smooth, uniform in diameter, and free from detrimental segregations, cracks, twists and kinks.

6.2 Finish — The wires shall be finished by such cold working and annealing operations as will produce the required temper and surface finish as agreed to between the purchaser and the manufacturer.

7. DIAMETERS AND TOLERANCES

7.1 The diameters and tolerances on the diameters of wires shall be in accordance with IS : 9861-1981*.

8. SAMPLING AND RETEST

8.1 In any consignment all the coils of wire of the same size, temper and manufactured by a single firm under essentially similar conditions of production shall be grouped together to constitute a lot.

8.2 Unless otherwise decided by mutual agreement between the purchaser and the supplier, each coil of wire shall be examined from each lot for freedom from defects (*see 6*) and for tolerances on diameters (*see 7*). Any coil found defective in accordance with the provisions of 6 and 7 shall be rejected.

8.3 Unless otherwise agreed by the supplier and the purchaser, either one test for chemical composition shall be conducted for each 50 kg or part thereof of wires in this lot or one test for 500 kg or part thereof of a lot comprising the same cast.

NOTE 1 — The material required for chemical analysis from each of the coils intended for testing shall be collected in accordance with IS : 1817-1961†.

NOTE 2 — When the size of the order does not permit grouping in the above quantities, the rate of testing shall be as agreed to between the purchaser and the supplier.

*Dimensions for wrought copper and copper alloy wire for general engineering purposes.

†Methods of sampling non-ferrous metals for chemical analysis.

IS : 4412 - 1981

8.3.1 If the results as obtained for each of the chemical characteristics satisfy the corresponding requirements under 4, the lot shall be considered as conforming to the chemical requirements of this specification.

8.3.2 If the test results fail to satisfy the requirements for any of the characteristics, two more tests for that characteristic shall be done on the sample in order to confirm that the analysis has been done properly. If both the test results satisfy the relevant requirements under 4 the lot shall be considered as conforming to the specification, otherwise not.

9. PACKING

9.1 The wires shall be coiled carefully and each length of the wire shall be made up into a separate coil of mass up to 50 kg. The inner diameter of the coil shall be as agreed to between the supplier and the purchaser.

9.2 The coils shall be suitably packed to avoid damage during transit.

10. MARKING

10.1 Suitable metallic tags and labels with markings made on them to show the temper of the material in addition to the name of the manufacturer, mass, length and any such information required by the purchaser, shall be attached to each coil of the material.

10.1.1 The coils of wire may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard, under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha
(Common to all Offices)

Regional Offices:

	Telephone
Central Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002	{ 331 01 31 331 13 75 36 24 99
*Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 2 18 43 3 16 41 41 24 42
Southern : C. I. T. Campus, MADRAS 600113	{ 41 25 19 41 29 16
†Western : Manakalaya, E9 MIDC, Marol, Andheri (East), BOMBAY 400093	6 32 92 95

Branch Offices:

*Pushpak', Nurmohamed Shaikh Marg, Khanpur, AHMADABAD 380001	{ 2 63 48 2 63 49
†Peenya Industrial Area 1st Stage, Bangalore Tumkur Road BANGALORE 560058	{ 38 49 50 38 49 50
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	6 67 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
53/5, Ward No 29, R.G. Barua Road, 5th Byelane, GUWAHATI 781003	3 31 77
5-8-56C L. N. Gupta Marg (Nampally Station Road), HYDERABAD 500001	23 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{ 6 34 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208005	{ 21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
T.C. No. 14/1421, University P.O., Palayam TRIVANDRUM 695035	{ 6 21 04 6 21 17

Inspection Offices (With Sale Point):

Pushpanjali, First Floor, 205-A West High Court Road, Shankar Nagar Square, NAGPUR 440010	2 51 71
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	5 24 35

*Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, Calcutta 700072

†Sales Office in Bombay is at Novelty Chambers, Grant Road, Bombay 400007

‡Sales Office in Bangalore is at Unity Building, Narasimharaja Square, Bangalore 560002

Reprography Unit, BIS, New Delhi, India

AMENDMENT NO. 1 JUNE 2004
TO
IS 4412 : 1981 SPECIFICATION FOR
COPPER WIRES FOR GENERAL ENGINEERING
PURPOSES

(First Revision)

(Page 3, clause 2.0, line 2) — Substitute 'IS 3288 (Part 3) : 1986†' for 'IS : 3288 (Part 1) - 1981†'.

(Page 3, footnote marked '†') — Substitute the following for the existing footnote:

†Glossary of terms relating to copper and copper alloys : Part 3 Wrought forms.'

(Page 4, clause 3.1, line 2) — Substitute 'IS 1387 : 1993*' for 'IS : 1387 - 1967*'.

(Page 4, footnote marked '*') — Substitute the following for the existing footnote:

*General requirements for the supply of metallurgical materials (second revision).'

(Page 4, clause 5.1, line 2) — Substitute 'IS 1608 : 1995 §' for 'IS : 2656-1964§'.

(Page 4, footnote marked '§') — Substitute the following for the existing footnote:

§Mechanical testing of metals — Tensile testing (second revision).'

(MTD 8)

Reprography Unit, BIS, New Delhi, India